


Exova Warringtonfire
Holmesfield Road
Warrington
WA1 2DS
United Kingdom

T : +44 (0) 1925 655116
F : +44 (0) 1925 655419
E : warrington@exova.com
W: www.exova.com



BS 476 Part 3: 2004



External Fire Exposure Roof Test

A Report To: Wonderbuilds Inc. Ltd

Document Reference: Additional Test report No. 395002

Date: 1st February 2018

Issue No.: 1

Page 1

Testing
Advising
Assuring



Executive Summary

Objective To determine the fire performance of the following product when tested in accordance with BS 476: Part 3: 2004

Generic Description	Product reference	Thickness	Weight per unit area or density
Flame retardant grade GRP coating over 18mm oriented strand board	"Firestop 20 Professional GRP System"	19.65 mm	13.44kg/m ²
Individual components used to manufacture composite:			
Top coat	Confidential	Not stated	0.5l/m ²
Base coat	Confidential	Not stated	1.0l/m ²
Glass reinforcement	Not stated	Not stated	450g/m ²
Substrate	"Sterling OSB 3"	18mm	10.8kg/m ²
Please see page 5 and 6 of this test report for the full description of the product tested			

Test Sponsor Wonderbuilds Inc. Ltd, Unit 3, Streakes Field Road, Staples Corner, London, NW2 7GD.

Test Results In Accordance With The Designations Defined In BS 476: Part 3: 2004 The Test Specimens Are In Category "EXT.F. AB".

Date of Test: 26th January 2015



This test report is additional to that issued as 348167 (issue 2) dated the 6th February 2015 and has been issued at the request of the sponsor. The original test report remains valid and is not replaced by this additional test report. The product referred to in the original report and this additional test report has not been re-tested since the original test and neither has a technical review of the original test report resulting in any technical changes been carried out.

The original product reference of the product has been removed and the reference "Firestop 20 Professional GRP System" has been inserted and the original sponsor name and address details have been removed and those of "Wonderbuilds Inc Ltd" have been inserted. The sponsor of the test has stated that the material described in this additional report is identical to the material which was tested. Both the original and the alternative trade names of the product and the original and alternative sponsor details have been documented and the documentation is maintained in the confidential file covering this investigation.

Document No.: Additional Test Report No. 395002 Page No.: 2 of 11
 Author: K. Hughes Issue Date: 1st February 2018
 Client: Wonderbuilds Inc. Ltd Issue No.: 1



Signatories

	
Responsible Officer K. Hughes * Technical Officer	Authorised T. Mort * Senior Technical Officer

* For and on behalf of **Exova Warringtonfire**.

Report Issued: 1st February 2018

This version of the report has been produced from a .pdf format electronic file that has been provided by **Exova Warringtonfire** to the sponsor of the report and must only be reproduced in full. Extracts or abridgements of reports must not be published without permission of **Exova Warringtonfire**.

CONTENTS	PAGE NO.
EXECUTIVE SUMMARY	2
SIGNATORIES.....	3
TEST DETAILS.....	5
DESCRIPTION OF TEST SPECIMENS.....	6
TEST RESULTS	8
TABLE 1	9
REVISION HISTORY	11



Test Details

Purpose of test	<p>To determine the performance of specimens of a roof construction when they are subjected to the conditions of the test specified in BS 476: Part 3: 2004, "British Standard Specification for Fire Tests on Building Materials and Structures - External Fire Exposure Roof Tests".</p> <p>The test was performed in accordance with the test procedures specified in BS 476: Part 3: 2004 and this report should be read in conjunction with that British Standard.</p>
Scope of test	<p>The tests are designed to enable measurement of:</p> <ul style="list-style-type: none"> a) capacity of a representative section of a roof to resist penetration by fire when the external surface is exposed to radiation and flame; and b) distance of the spread of flame on the outer surface of the roof covering under certain conditions. <p>Roofs are graded according to the angle at which they are tested, the time for which they resist penetration by fire and the distance of superficial spread of flame on their external surface.</p> <p>The test specimens are tested at an angle of 45° to the horizontal (sloping position) unless the roof construction is used at an angle of less than 10° to the horizontal, in which case the specimens are tested horizontally (flat position).</p>
Fire test study group/EGOLF	<p>Certain aspects of some fire test specifications are open to different interpretations. The Fire Test Study Group and EGOLF have identified a number of such areas and have agreed Resolutions which define common agreement of interpretations between fire test laboratories which are members of the Groups. Where such Resolutions are applicable to this test they have been followed.</p>
Instruction to test	<p>The test was conducted on the 26th January 2015 at the request of the original sponsor of the test.</p>
Provision of test specimens	<p>The specimens were supplied by the original sponsor of the test. Exova Warringtonfire was not involved in any selection or sampling procedure.</p>
Conditioning of specimens	<p>The specimens were received on the 8th January 2015. Prior to testing the specimens were conditioned to equilibrium in an atmosphere having a temperature of 23 ±2°C and a relative humidity of 45 to 55%.</p>
Orientation of specimens	<p>The specimens were tested in the flat position.</p>

Description of Test Specimens

The description of the specimens given below has been prepared from information provided by the original sponsor of the test. All values quoted are nominal, unless tolerances are given.

General description		Flame retardant grade GRP coating over 18mm orientated strand board
Product reference		"Firestop 20 Professional GRP System"
Name of manufacturer		Confidential
Thickness		19.65 mm (Stated by sponsor) 20.04mm (determined by Exova Warringtonfire)
Weight per unit area		13.44kg/m ² (Stated by sponsor) 13.02kg/m ² (determined by Exova Warringtonfire)
Top coat	Generic type	Pigmented polyester
	Product reference	Confidential
	Name of manufacturer	Confidential
	Colour reference	"Dark Admiralty Grey"
	Number of coats	One
	Application rate	0.5l/m ²
	Specific gravity	1.32
	Application method	Roller
	Curing process per coat	Ambient temperature cure
	Flame retardant details	See Note 1 Below
Base coat	Generic type	Polyester resin
	Product reference	Confidential
	Name of manufacturer	Confidential
	Colour reference	"Non Pigmented"
	Number of coats	One
	Application rate	1.0l/m ²
	Specific gravity	1.17
	Application method	Roller
	Curing process per coat	Ambient temperature cure
	Flame retardant details	See Note 1 Below

Continued on next page

Glass reinforcement	Generic type	Emulsion bound chopped strand mat
	Product reference	See Note 2 Below
	Number of layers	One
	Weight per unit area of each layer	450g/m ²
	Configuration of glass reinforcement	Random
	Name of manufacturer	See Note 2 Below
	Flame retardant details	See Note 2 Below
Substrate	Generic type	Oriented strand board
	Product reference	"Sterling OSB 3"
	Timber species	See Note 3 Below
	Thickness	18mm
	Weight per unit area	10.8kg/m ²
	Name of supplier	Norbord Ltd
	Flame retardant details	See Note 3 Below
Brief description of manufacturing process		Batch blending process of resins. Roller application of resins to substrate.

Note 1: The sponsor of the test has provided this information but at the specific request of the sponsor, these details have been omitted from the report and are instead held on the confidential file relating to this investigation.

Note 2: The sponsor was unwilling to provide this information.

Note 3: The sponsor was unable to provide this information.

Test Results

Results

The test results relate only to the behaviour of the test specimens of the construction under the particular conditions of test, they are not intended to be the sole criterion for assessing the potential fire hazard of the construction in use.

The test results relate only to the specimens of the roof construction which were tested. Small differences in the composition or thickness of the construction may significantly affect the results of the test and may therefore invalidate the test results. Care should be taken to ensure that any construction which is supplied or used is fully represented by the specimens which were tested.

The results of the tests on each of the specimens are given in Table 1.

In Accordance With The Designations Defined In BS 476: Part 3: 2004 The Test Specimens Are In Category “EXT.F. AB”.

Validity

The specification and interpretation of fire test methods are the subject of ongoing development and refinement. Changes in associated legislation may also occur. For these reasons it is recommended that the relevance of test reports over five years old should be considered by the user. The laboratory that issued the report will be able to offer, on behalf of the legal owner, a review of the procedures adopted for a particular test to ensure that they are consistent with current practices, and if required may endorse the test report.

This report may only be reproduced in full. Extracts or abridgements shall not be published without permission of **Exova Warringtonfire**.

Table 1

PRELIMINARY IGNITION TEST WITH BURNING BRANDS (STAGE 1)	Specimen No:		
		1	
Room temperature at start of test (°C)	26		
Time to fire penetration (if applicable) (min:sec)	N/A		
Duration of flaming after withdrawal of the test flame (if applicable) (min:sec)	Nil		
Maximum flame spread distance (if applicable) (mm)	Nil		

SPREAD OF FLAME TEST WITH BURNING BRANDS AND SUPPLEMENTARY RADIANT HEAT (STAGE 2)	Specimen No:		
	2	3	4
Room temperature at start of test (°C)	22	27	27
Duration of flaming after withdrawal of the test flame (if applicable) (min:sec)	53:04	55:59	53:20
Maximum flame spread distance (if applicable) (mm)	240	340	360
Additional observations:			
In the case of all three specimens ignition occurred in the first minute of the test.			

PENETRATION TEST WITH BURNING BRANDS, WIND AND SUPPLEMENTARY RADIANT HEAT (STAGE 3)	Specimen No:		
	5	6	7
Room temperature at start of test (°C)	27	28	28
Time to fire penetration (if applicable) (min:sec)	Did not penetrate	Did not penetrate	Did not penetrate
Additional observations:			
In the case of all three specimens no ignition occurred.			

Classification Of Specimens

The following is reproduced from Clause 4 of BS 476: Part 3: 2004.

4 Classification

4.1 Roof system

Roof systems shall be designated by the letters EXT.F or EXT.S to indicate whether the test results apply to a flat (horizontal) or an inclined roof system, respectively

4.2 Fire Resistance of roof system

4.2.1 Coding system

Roof systems subject to conditions of external fire shall be classified according to both the time of penetration and the distance of spread of flame along their external surface.

Each category designation shall consist of two letters, e.g. AA, AC, BB, these being determined as specified in 4.22 and 4.23

4.2.2 Fire penetration (first letter)

- A. Those specimens that have not been penetrated within one hour
- B. Those specimens that are penetrated in not less than 30 min.
- C. Those specimens that are penetrated in less than 30 min.
- D. Those specimens that are penetrated in the preliminary flame test

4.2.3 Spread of flame (second letter)

- A. Those specimens on which there is no spread of flame
- B. Those specimens on which the spread of flame is less than or equal to 533mm, with averaged results rounded up or down to the whole number, as normally practised
- C. Those specimens on which the spread of flame is greater than 533mm, with averaged results rounded up or down to the whole number, as normally practised
- D. Those specimens that continue to burn for five minutes after withdrawal of the test flame or spread more than 381mm across the region of burning in the preliminary test.

4.2.4 Suffix "X"

Attention shall be drawn to dripping from the underside of the specimen, any mechanical failure, and any development of holes, by adding a suffix "X" to the designation to denote that one or more of these took place during the test.

EXAMPLE 1 EXT.F.AA is a flat roofing system with one hour fire penetration resistance on which there was no spread of flame.

EXAMPLE 2 EXT.S.CCX is an inclined roofing system with less than 30 min fire penetration resistance, on which the spread of flame exceeded 533mm and further deterioration took place.

Revision History

Issue No :	Issue Date:
Revised By:	Approved By:
Reason for Revision:	

Issue No :	Issue Date:
Revised By:	Approved By:
Reason for Revision:	