

WONDERBUILDS BROOFT4 CAP SHEET

Waterproofing membrane

PRODUCT DESCRIPTION

WONDERBUILDS BROOFT4 CAP SHEET is a prefabricated waterproofing membrane made of distilled bitumen and elasto-plastomeric polymers (APP). The capsheet versions have a non-woven single strand composite polyester reinforcement, with good mechanical characteristics and excellent dimensional stability. WonderBuilds Brooft4 Cap Sheet are self-protected on the upper face with mineral slates, which reduce superficial heat absorption improving the durability of the membrane. The self-protected versions have a side selvedge of 10cm and upon request a head selvedge of 15cm, to improve adhesion between the sheets.

PRODUCT FEATURES

Torch-on application

Fire-resistant

Outstanding performance at high temperature and good at low temperature

High quality polyester carrier

Part of the Brooft4 system

METHODS OF APPLICATION

For the application of the membrane the use of heat is generally used by means of a gas torch or specific hot air machine.

The application by heat is not suggested when on heat sensitive materials (polystyrene insulation).

- Coordinate the operations in a way that does not cause damage to the construction elements and underground structure. Avoid leaving the structure for the night or for periods of prolonged work interruptions without having been properly sealed.
- **The application surface must not have any depressions to avoid the risk of ponding water, the slope must be at least 1.5% on concrete decks and 3% for steel or wooden ones, to guarantee a proper run off of rainwater.**
- The water drainage spouts should be sufficiently big enough to allow for rainwater to be eliminated in an efficient way.
- Prepare cementitious substrates, including verticals and details, with a bituminous primer either by brush or airless, approx. 300/400 g/m².
- Allow this preparation layer to dry before proceeding with any other operation.
- With prefabricated constructions, apply a suitable reinforcing strip along all joints. In the presence of construction joints, prefabricated panels or metal decks, suitable expansion joints are to be considered.
- The membranes must be applied to the substrate fully bonded.
- All details, perimeters, verticals, change of slope as well as projecting area must be fully bonded.

FIELDS OF USE

	CONTINUOUS ROOF EN13707																
	N. LAYERS			METHODS OF APPLICATION						TYPE OF APPLICATION			TYPE				
	SINGLE LAYER	DOUBLE LAYER	MULTILAYER	TORCH	HOT AIR	MIXED (TORCH/AIR)	COLD BOND GLUE	MECHANICAL FIXINGS	THERMO AD / SELF ADHESIVE	FULLY BONDED	PARTIALLY BONDED	LOOSE LAID	COMPLIMENTARY LAYER	TOP LAYER	HEAVY PROTECTION	ANTI-ROOT	OTHER USES
WONDERBUILDS BROOFT4 CAP SHEET		•	•	•						•				•			
UNDER ROOF TILE EN13859-1																	
WONDERBUILDS BROOFT4 CAP SHEET	•	•	•	•						•				•			



APPLICATION

- On cementitious surfaces and applied by roller or airless, bituminous primer, approx. consumption 300 g/m².
- Apply by torch application a 25cm strip of membrane reinforced with polyester along all vertical up stands.
- To have all overlaps with the slope, position the membrane always starting from the lowest point.
- Position the membrane sheets staggered, avoiding any overlaps against the slope and the drains.
- Cut the corners of membrane sheet, which will be laid under the next sheet at a 45° angle (10 x 10cm).
- The joints, both side and head, must be respectively overlapped by 10 & 15cm.
- The second layer of membrane will be applied astride and over the first one, always in the same direction, and approx. 1/4 of its length from the previous sheet.
- The bituminous membrane will be applied with a propane gas torch to the substrate. It is necessary to heat the entire surface, except for the side & head laps, making sure that the compound forms a liquid mass in front of the roll to assure that it saturates any superficial porosity.
- The side laps (10cm) and head laps (15cm) will be heat welded with an appropriate torch; during this stage, the overlaps should be pressed by using a roller (15kg) from which a bead of compound should flow and therefore avoiding the iron from overlapping.
- Apply the vertical membrane sheet having the same characteristics of the waterproofing membrane and dimensions equal to the width of the roll, making sure that it overlaps the horizontal one by at least 10cm, heating it with a gas torch and squeezing it with a trowel until a bead of compound appears from underneath.
- The height of the verticals must be equivalent or superior to the finished surface by at least 15cm.

RECOMMENDATIONS

To best use the technical characteristics of bituminous membranes and guarantee the maximum performance and durability of the jobs where they are used, some simple but fundamental rules must be respected.

- The rolls are to be stored in an upright position, indoors in a dry and ventilated area, away from heat sources. Absolutely avoid the stacking of rolls and pallets for storage or transport to avoid possible deformations which may compromise a perfect installation. It is recommended to store the product at temperatures above 0°C.
- The rolls shall be kept in a warm or heated storage area during application, should the workability of the material deteriorate or become stiff and difficult to install during application, these should be returned to the heated storage area and substituted with new rolls. The rolls that are temporarily stored on the roof before application, shall be kept elevated by being left on their own pallets and shall be covered and protected from the weather.
- The application surface must be smooth, dry & clean.
- The application surface must be previously treated with a suitable bituminous primer, to eliminate dust and enhance the adhesion of the membrane.
- The application surface must not have any depressions to avoid the risk of ponding water, the slope must be at least 1.5% on concrete decks and 3% for steel or wooden ones, this to guarantee a proper run off of rainwater.
- In situations of application on vertical surfaces superior to 2 meters or on very sloped substrates, apply suitable mechanical fixings to the head laps, after which they will be sealed when torching the head laps.
- The application must be done at a temperature higher than +5°C.
- The application must be interrupted in adverse weather conditions (high humidity, rain, etc.).
- The pallets on which the rolls are packaged are intended for normal warehouse use.
- The materials on stock should be rotated following a first in first out rotation.
- For further information it is recommended to consult our Installation Manual.

Product Name	Product Code	Roll Dimensions (m)	Weight (kg/m ²)
WONDERBUILDS BROOFT4 CAP SHEET	A0005640	8 x 1	4.5

Technical Data	Measure Units	Test Method	Results	Tolerance
Type of compound			APP	
Type of reinforcement			Polyester	
Upper face finish			Black Mineral*	
Lower face finish			PE film	
Length	m	EN 1848-1	8 -1%	
Width	m	EN 1848-1	1 -1%	
Mass	kg/m ²	EN 1849-1	4,5	±10%
Cold flexibility	°C	EN 1109	-15	
Flow resistance	°C	EN 1110	140	
Flow resistance after ageing	°C	EN 1296	130	
Tensile strength L/T	N/5 cm	EN 12311-1	700 / 500	±20%
Elongation at break L/T	%	EN 12311-1	30 / 30	±15
Tearing resistance L/T	N	EN 12310-1	200 / 200	±30%
Dimensional stability	%	EN 1107-1	-0,2	
Loss mineral	%	EN 12039	30	
Fire resistance		EN 13501-5	B _{ROOF} (t4)	
Fire reaction		EN 13501-1	E	
Tensile strength after ageing L/T	N/5 cm	EN 1296	NPD	±20%
Impermeability after artificial ageing	kPa	EN 1296	60	
Watertightness	kPa	EN 1928	60	

* Mineral self-protected products may undergo color tone variations due to the time and length of storage. Exposure to atmospheric conditions, after application, will tend to uniform the color after a few months. The change in color tone cannot therefore be contested and / or complained of as it is a natural phenomenon that the slate manufacturer himself cannot guarantee.

NPD = No Performance Declared in accordance with the EU Construction Products Directive.

Technical Service And Other Products

Specialist advice and information on other compatible products can be found at www.wonderbuilds.co.uk.