

POLY-ELAST RAPID O

Bituminous Single Layer Universal Membrane

Introduction

POLY-ELAST RAPID O is a single layer, bituminous membrane which is saturated and coated with high quality SBS (Styrene-Butadiene-Styrene) modified bitumen. It has a 180g/m² composite reinforcement and incorporates a special graphite additive within the coating to provide exceptional fire protection properties. The membrane's design also incorporates diagonal shaped channels on the underside which help to vent and control any entrapped roof moisture and enable the product to be rapidly installed using a variety of methods.

Product Description

POLY-ELAST RAPID O provides a cost-effective, fast-track method of overlaying existing roof coverings to provide a reliable, long-lasting waterproofing solution. The product is compatible with all common bituminous and asphaltic substrates.

Product Features

- Cost-effective overlay solution
- Graphite technology which actively prevents spread of flames on roof
- Excellent low temperature flexibility at -25°C
- Versatile methods of application
- Robust, thick product – highly resistant to site foot traffic

Application

POLY-ELAST RAPID O should be installed in accordance with manufacturer recommendations and all relevant national standards and codes of practice, including BS 8217: 2005 – the code of practice for reinforced bitumen membranes for roofing.

Roofing contractors should also be fully conversant with the guidelines set out in the National Federation of Roofing Contractors (NFRC) 'Safe2Torch' campaign. All operatives using torch guns or hot air guns during installation should be competent, conversant and capable of using such items in a safe and responsible manner. Care must also be taken when using torches and hot air guns near combustible materials, decorative coatings and heat sensitive materials. When setting out the field area, rolls should always be laid in the same direction. Side lap width should be at least 8cm with end laps of at least 10 cm.

POLY-ELAST RAPID O can be rapidly installed using a variety of methods. Most commonly it will be torch- applied to the existing substrate surface, but the membrane can also be installed using a heat gun or can be bonded in PU adhesive depending on client preference and project requirements. For detailed installation guidelines using any of these methods, please consult WonderBuilds Technical Services.

NB: The colour of the granules may vary during their useful life because of the weather and other outside agents.

Chemical Resistance

POLY-ELAST RAPID O is water-resistant and is resistant to watery solutions of salt, diluted non-oxidising acids and bases. Aliphatic and aromatic hydrocarbons, as well as chlorine hydrocarbons, oils and greases may loosen the product and should therefore be avoided.

Storage

Store in a cool, dry place and protect from direct sunlight

Health and Safety

Health and Safety should be observed at all times in accordance with HSE and industry guidance. Specific Risk Assessments and Method Statements should be produced by contractors where necessary to ensure Working at Heights, Fire Safety and Manual Handling rules are compliant with current law and regulations. Health and safety data sheets are available for all materials on request from WonderBuilds Technical Service Department.

Quality Assurance

POLY-ELAST RAPID O is manufactured following ISO 9001: 2008 Quality Management System and Environmental Management System approved to ISO 14001: 2004

Further Information

View our full range of products at www.wonderbuilds.co.uk. You can also contact us at 0208 208 2121, or at admin@wonderbuilds.co.uk.

Availability

Product Name	Product Code	Roll Dimensions (m)	Weight (kg/m ²)
POLY-ELAST RAPID O (Anthracite)	SBSM0024	5.0 x 1.00	6.0

*Specification systems only – please contact WonderBuilds for further details

Performance

Properties	Test Method		Declared Performance
Length	DIN EN 1848-1	m	≥ 5.00
Width	DIN EN 1848-1	m	≥ 1.00
Straightness	DIN EN 1848-1	mm/10 m	≤ 20
Mass per unit area	DIN EN 1849-1	kg/m ²	6.0 (± 5%)
Thickness	DIN EN 1849-1	mm	5.00 (± 5%)
Water tightness at 200 kPa test pressure	DIN EN 1928 Method B	-	passed
External fire performance	DIN V ENV 1187	-	see testing of system
Reaction to fire	DIN EN 11925-2	-	Class E according to DIN EN 13501-1
Tensile properties: maximum tensile force	DIN EN 12311-1	N/50mm	800/700 (± 10%)
Tensile properties: elongation	DIN EN 12311-1	%	30/30 (± 5 abs)
Flexibility at low temperatures	DIN EN 1109	° C	≤ - 25
Flow resistance at elevated temperatures	DIN EN 1110	° C	≥ + 110