

WONDERBUILDS 6KG A BLACK CAP SHEET 8M

Description

WONDERBUILDS 6KG A BLACK CAP SHEET 8M is an elastomeric Modified Bitumen Membrane used for various waterproofing applications. It is manufactured in a high-tech calendaring process, which involves the saturation and coating of a polyester carrier with a SBS elastomer-modified bitumen compound. The SBS modifiers are used to improve the thermal, chemical, and ageing properties of the bitumen compound. Meanwhile, the mechanical characteristics such as tensile strength, elongation and tear resistance are boosted by the non-woven polyester carrier, which acts as a reinforcement to the product

Product Features

- Excellent U.V. resistance if finished with slated
- Superior chemical resistance to alkaline solutions, light acidic solutions, and bacteria
- Superior thermal resistance under a wide range of temperature fluctuation
- Absolute impermeability to water
- Outstanding performance at high temperature and good at low temperature
- Excellent adhesion to any surface
- Applicable for above and below grades usages

Application

The membranes are used for a wide variety of waterproofing requirements and in applications subject to high mechanical stresses, such as:

- roofing or re-roofing for single or multi-layer systems
- sloped and flat roofs
- tunnels, wet areas, swimming pools and toilets
- foundations and underground structures
- slab on grade

Performance

Technical Data	Measure Units	Reference Norm	Properties	Tolerance
Type of Compound			SBS	
Length	m	EN 1848-1	8	MDV \pm 1%
Width	m	EN 1848-1	1	MDV \pm 1%

Mass	kg/m ²	EN 1849-1	6	MDV ± 5%
Cold flexibility	°C	EN 1109	-22 to -25	MLV ≤
Flow resistance	°C	EN 1110	110	MDV - 10
Tensile strength L/T	N/5 cm	EN 12311-1	900 / 650	MDV ± 20%
Elongation at break L/T	%	EN 12311-1	45 / 50	MDV ± 15
Resistance to Static Loading	kg	EN 12730	20	MLV ≤
Resistance to Impact Loading	mm	EN 12691	1250	MLV ≤
Dimensional stability	%	EN 1107-1	± 0.5	
Fire resistance		EN 13501-5	F Roof	
Fire reaction		EN 13501-1	F	
Watertightness	10 kPa	EN 1928:2000	PASS	
Water Vapour Transmissions	μ	EN 1931	20000	
Average Lose of Slated	%	EN 12039	30	MLV ≤

Availability

Product Name	Product Code	Roll Dimensions (m)	Weight(kg/m ²)
WONDERBUILDS 6KG A BLACK CAP SHEET 8M	WB6ABM	8 x 1	6

Surface Finish

The lower surface of the membrane is laminated with a thin thermo-fusible polyethylene 'burn-off' film. The upper face is protected with mineral slates.

Storage

This product should be stored in an upright position in a dry, flat, and ventilated storage area away from direct sunlight.

Further Information

View our full range of products at www.wonderbuilds.co.uk

You can also contact us at [0208 208 2121](tel:02082082121), or at admin@wonderbuilds.co.uk